

Amendments to the Claims: This listing of claims will replace all prior versions, and listings, of claims in the application.

Listing of Claims:

1. (Currently amended) A three-dimensional construct comprising: a polymeric matrix; and a particle ~~comprising having~~ a chemical functional group attached thereto, wherein the ~~nanoparticle-particle~~ has a diameter of about 5 nm to about 10 microns and is (a) coated with ~~a~~ at least one monomolecular layer comprising biological information and (b) dispersed in the polymeric matrix at a density of at least 0.01 vol%.
2. (Previously presented) The three-dimensional construct of claim 1, wherein the monomolecular layer is attached to the particle by at least one of covalent bonding, hydrogen bonding, ionic bonding, Van der Waals forces and ligand-substrate binding.
3. (Previously presented) The three-dimensional construct of claim 1, wherein the monomolecular layer comprises a plurality of sequentially arranged monomolecular layers, wherein an innermost monomolecular layer is attached to the particle and an outermost monomolecular layer is external to the innermost layer, provided that (a) the innermost monomolecular layer is attached to the particle by at least one of covalent bonding, hydrogen bonding, ionic bonding, Van der Waals forces and ligand-substrate binding.
4. (Currently amended) The three-dimensional construct of claim 1, wherein the particle is coated with a plurality of monomolecular layers ~~includes comprising~~ (a) ~~the-an~~ innermost monomolecular layer that is attached to or in contact with the particle, (b) ~~an-at least one~~ intermediate monomolecular layer and (c) ~~the-an~~ outermost monomolecular layer, wherein ~~the-at least one~~ intermediate monomolecular layer is attached to ~~at least one of the~~ innermost monomolecular layer and at least one intermediate monomolecular layer is attached to the outermost monomolecular layer, provided that at least two of the plurality of the monomolecular layers are attached to each other by at least one of covalent bonding, hydrogen bonding, ionic bonding, Van der Waals forces and ligand-substrate binding.
5. (Original) The three-dimensional construct of claim 1, wherein the biological information is a member selected from the group consisting of a biomolecule, a polymer, and a bone substitute.

6. (Original) The three-dimensional construct of claim 5, wherein the biomolecule is a member selected from the group consisting of a bioactive polypeptide, a polynucleotide coding for the bioactive polypeptide, a cell regulatory small molecule, a peptide, a protein, an oligonucleotide, a nucleic acid, a poly(saccharide), an adenoviral vector, a gene transfection vector, a drug, and a drug delivering agent.

7. (Original) The three-dimensional construct of claim 6, wherein the bioactive polypeptide is a growth factor and such growth factor is a member selected from the group consisting of an epidermal growth factor, an acidic fibroblast growth factor, a basic fibroblast growth factor, a glial growth factor, a vascular endothelial growth factor, a nerve growth factor, a chondrogenic growth factor, a platelet-derived growth factor, a transforming growth factor beta, an insulin-like growth factor, a hepatocyte growth factor, a brain derived growth factor, bone morphogenic proteins and osteogenic proteins.

8. (Original) The three-dimensional construct of claim 5, wherein the polymer is a member selected from the group consisting of poly(carboxylic acid), poly(sulphonic acid), poly(lysine), and poly(allylamine).

9. (Original) The three-dimensional construct of claim 8, wherein the poly(carboxylic acid) is poly(acrylic acid).

10. (Previously presented) The three-dimensional construct of claim 1, wherein the chemical functional group is a member selected from the group consisting of an amine group, a hydroxyl group, a carboxy group, an $-\text{OSO}_3\text{H}$ group, a $-\text{SO}_3\text{H}$ group, a $-\text{SH}$ group, an $-\text{OCN}$ group, a phosphorous group, an epoxy group, a vinylic moiety, a silane coupling agent, an acrylate, a methylacrylate, and a metal alkoxo group.

11. (Original) The three-dimensional construct of claim 5, wherein the bone substitute is a member selected from the group consisting of a calcium phosphate, a bioactive glass composition and a bioceramic.

12. (Original) The three-dimensional construct of claim 11 wherein the calcium phosphate is a member selected from the group consisting of hydroxyapatite, tricalcium phosphate, tetracalcium phosphate, and octacalcium phosphate.

13. (Cancelled)

14. (Currently amended) The three-dimensional construct of claim ~~13~~1, wherein the ~~inorganic structure is a member~~particle comprises a compound selected from the group consisting of an oxide, a nitride, a carbide, calcium silicate, calcium phosphate, calcium carbonate, a carbonaceous material, a metal, and a semiconductor.

15. (Currently amended) The three-dimensional construct of claim 14, wherein the ~~particle comprises an oxide is a member~~ selected from the group consisting of Al_2O_3 , TiO_2 , ZrO_2 , Y_2O_3 , SiO_2 , ferric oxide, ferrous oxide, a rare earth metal oxide, a transitional metal oxide, mixtures thereof and alloys thereof.

16. (Currently amended) The three-dimensional construct of claim ~~15~~14, wherein the ~~particle comprises a metal is a member~~ selected from the group consisting of aluminum, gold, silver, stainless steel, iron, titanium, cobalt, nickel, and alloys thereof.

17. (Currently amended) The three-dimensional construct of claim ~~13~~1, wherein the ~~organic structure~~particle comprises is a member~~material~~ selected from the group consisting of biodegradable polymers, non-biodegradable water-soluble polymers, non-biodegradable non-water soluble polymers, lipophilic moieties, and biopolymers.

18. (Currently amended) The three-dimensional construct of claim 17, wherein the ~~organic structure is a member~~particle comprises a material selected from the group consisting of poly(styrene), poly(urethane), poly(lactic acid), poly(glycolic acid), poly(ester), poly(alpha-hydroxy acid), poly(e-caprolactone), poly(dioxanone), poly(orthoester), poly(ether-ester), poly(lactone), poly(carbonate), poly(phosphazene), poly(phosphonate), poly(ether), poly(anhydride), mixtures thereof and copolymers thereof.

19. (Original) The three-dimensional construct of claim 1, wherein the polymeric matrix is a member selected from the group consisting of alginate, hyaluronic acid, poly(ethylene glycol), poly(vinyl alcohol), collagen, a peptide, poly(ethylene oxide)-b-poly(propylene oxide)-b-poly(ethylene oxide), poly(acrylic acid), and poly(isopropyl amide).

20. (Original) The three-dimensional construct of claim 19 wherein the three-dimensional construct is in a form of a gel, a cross-linked polymer, a liquid, a foam, a sponge, a mesh, a solid particulate, a fiber, or a layer.

21. (Original) The three-dimensional construct of claim 1, further comprising a cell dispersed within the polymeric matrix, wherein the cell is a member selected from the group consisting of chondroblast, chondrocyte, fibroblast, an endothelial cell, osteoblast, osteocyte, an epithelial cell, an epidermal cell, a mesenchymal cell, a hemopoietic cell, an embryoid body, a stem cell, and dorsal root ganglia.

22. (Currently amended) The three-dimensional construct of claim 1, wherein the nanoparticle particle comprises silicon oxide, the chemical functional group comprises an amine group and the monomolecular layer comprises hydroxyapatite.

23. (Original) The three-dimensional construct of claim 22, wherein the monomolecular layer comprises at least one of a monomolecular layer of poly(acrylic acid) and a monomolecular layer of collagen as the intermediate monomolecular layer, provided that the monomolecular layer comprising hydroxyapatite is the outermost monomolecular layer.

24. (Original) The three-dimensional construct of claim 22, wherein the polymeric matrix is alginate, poly(ethylene glycol), poly(vinyl alcohol), collagen, a peptide, or poly(ethylene oxide)-b-poly(propylene oxide)-b-poly(ethylene oxide).

25. (Currently amended) The three-dimensional construct of claim 1, wherein the nanoparticle particle comprises at least one of poly(lactic acid), poly(lactic-co-glycolic acid), and poly(anhydride) and the monomolecular layer comprises at least one of the monomolecular layer of poly(acrylic acid) and the monomolecular layer of collagen as the innermost monomolecular layer and the monomolecular layer of hydroxyapatite as the outermost monomolecular layer.

26. (Withdrawn) A method of presenting biological information to a cell or a tissue, the method comprising: providing the three-dimensional construct of claim 1; and contacting the three-dimensional construct with the cell or the tissue to present the biological information and thereby affecting the at least one characteristic of the cell or the tissue.

27. (Withdrawn) The method of claim 26, wherein the diameter, the biological information and the density are selected to affect the at least one characteristic of the cell or the tissue.

28. (Withdrawn) The method of claim 26, wherein the monomolecular layer is attached to the nanoparticle by at least one of covalent bonding, hydrogen bonding, ionic bonding, Van der Waals forces and ligand-substrate binding and when the plurality of the monomolecular layers is provided, the monomolecular layers are attached to each other by at least one of covalent bonding, hydrogen bonding, ionic bonding, Van der Waals forces and ligand-substrate binding.

29. (Withdrawn) The method of claim 26, wherein the biological information is a member selected from the group consisting of a biomolecule, a polymer, and a bone substitute.

30. (Withdrawn) The method of claim 26, wherein the nanoparticle comprises an inorganic structure or an organic structure.

31. (Withdrawn) The method of claim 26, wherein the at least one characteristic of the cell or the tissue is proliferation or differentiation.

32. (Withdrawn) The method of claim 26, wherein the nanoparticle comprises silicon oxide, the chemical functional group comprises an amine group and the monomolecular layer comprises hydroxyapatite.

33. (Withdrawn) The method of claim 32, wherein the monomolecular layer comprises at least one of a monomolecular layer of poly(acrylic acid) and a monomolecular layer of collagen as the intermediate monomolecular layer, provided that the monomolecular layer comprising hydroxyapatite is the outermost monomolecular layer.

34. (Withdrawn) The method of claim 33, wherein the polymeric matrix is an alginate, poly(ethylene glycol), poly(vinyl alcohol), collagen, a peptide, or poly(ethylene oxide)-b-poly(propylene oxide)-b-poly(ethylene oxide).

35. (Withdrawn) The method of claim 33, wherein the hydroxyapatite is deposited onto collagen from an aqueous mixture comprising calcium nitrate tetrahydrate and ammonium phosphate at a molar ratio about 1.5 to about 2 and pH of about 7 to about 9.5.

36. (Withdrawn) The method of claim 35, wherein the molar ratio is equal 2.

37. (Withdrawn) The method of claim 26, wherein the nanoparticle comprises at least one of poly(lactic acid), poly(lactic-co-glycolic acid), and poly(anhydride) and the monomolecular layer comprises at least one of the monomolecular layer of poly(acrylic acid) and the monomolecular layer of collagen as the innermost monomolecular layer and the monomolecular layer of hydroxyapatite as the outermost monomolecular layer.

38. (Withdrawn) The method of claim 27, further comprising contacting the three-dimensional construct of claim 1 with an auxiliary surface prior to contacting the three-dimensional construct with the cell or the tissue.

39. (Withdrawn) The method of claim 38, wherein the auxiliary surface is a member selected from the group consisting of a polymer, a carbonaceous material, a wool, a glass, a ceramic, and a metal.

40. (Withdrawn) The method of claim 39, wherein the auxiliary surface is in a shape of a mesh, a fiber, a sheet, a sponge, a layer, a pattern, and a pre-formed object.

41. (Withdrawn) The method of making the three-dimensional construct of claim 1, the method comprising: providing the polymeric matrix; providing an unprocessed nanoparticle; making the nanoparticle by contacting the unprocessed nanoparticle with a carrier of biological information to form the monomolecular layer; and dispersing the nanoparticle in the polymeric matrix at the density of at least 0. vol. % and thereby making the three-dimensional construct.

42. (Withdrawn) The method of claim 41, further comprising providing a hardening agent.

43. (Withdrawn) A nanoparticle comprising: a structure, said structure is being a member selected from the group consisting of silicon oxide functionalized with a chemical

functional group, poly(lactic acid), poly(lactic-co-glycolic acid), and poly(anhydride); a monomolecular layer of hydroxyapatite; and optionally a monomolecular layer of poly(acrylic acid) and/or a monomolecular layer of collagen, wherein the structure is coated with the monomolecular layer of hydroxyapatite and optionally with the monomolecular layer of poly(acrylic acid) and/or the monomolecular layer of collagen, provided that the monomolecular layer of hydroxyapatite is an outermost monomolecular layer.

44. (Withdrawn) The nanoparticle of claim 43, wherein the chemical functional group is a member selected from the group consisting of an amine group, a hydroxyl group, a carboxy group, an -OSO₃H group, a -SO₃H group, a -SH group, an -OCN group, a phosphorous group, an epoxy group, a vinylic moiety, a silane coupling agent, an acrylate, a methylacrylate, a metal alkoxy group, and derivatives thereof.

45. (Withdrawn) The nanoparticle of claim 43, further comprising an auxiliary surface, said auxiliary surface is a member selected from the group consisting of a polymer, a carbonaceous material, wool, glass, ceramic, and a metal, and wherein said carrier is in communication with the nanoparticle.

46. (Withdrawn) The nanoparticle of claim 46, wherein the auxiliary surface is in a form of a gel, a liquid, a foam, a solid, a fiber, a mesh, a sheet, a sponge, a pattern, and a pre-formed object.

47. (Withdrawn) A method of administering the nanoparticle of claim 45 to a cell, the method comprising: providing the nanoparticle; optionally providing an auxiliary surface, wherein the auxiliary surface is a member selected from the group consisting of a polymer, a carbonaceous material, a wool, a glass, a ceramic, and a metal and wherein the auxiliary surface is in communication with the nanoparticle; and contacting the cell with the nanoparticle and thereby administering the nanoparticle.